### **Type**

Fast drying and odourless glazing paint for treating wood surfaces in sauna and washroom areas. Does not contain plastic agents. Ilona Sauna Stain leaves the grains of the wood visible and gives a surface that protects from moisture and dirt.

#### Intended use

For old and new untreated wood surfaces and surfaces that have been treated with glazing agents that do not form a hard coating, e.g. sauna and washroom ceilings and wall panels, doors, window frames and benches. The product is not suitable for surfaces that have been previously treated with paraffin oil or wax.

Do not use on floors.

## **Technical qualities**

Gloss grade: Silky matt. Density 1.05 kg/L.

Emission class M1 in building materials.

Wet abrasion resistance: over 5000 strokes. Washable.

Does not contain any VOC.

Non-flammable.

#### **Colours**

Colourless, can be tinted according to the translucent colours of Jula interior colour chart. Can also be tinted according to most common colour charts.

## **Application & conditions**

Lacquer brush, levelling paint brush or ordinary paint brush.

The surface to be painted must be dry, the relative air humidity below 80 % and the temperature at least +10°C.

# **Drying time**

Tack-free in approx. 30 minutes. A new coat of paint can be applied after 2 hours. (At 20°C and 80 % relative humidity).

Drying of the Sauna benches: Can be used after 1 week of painting.

# Coverage

Planed/smooth timber 12-15 m2/L

#### **Thinner**

Water

## **Cleaning of equipment**

Clean the equipment with soap and water right after you have finished painting.

#### **Container sizes**

0.9 L, 2.7 L, 9 L

## Storage & disposal

Keep in a cool and dry place. Do not allow to freeze! Dry and empty containers can be taken to a refuse dump. Liquid waste must be taken to a municipal hazardous waste collection point



## **Painting instructions**

## **Preparation**

Remove dust from the surface to be treated. Wash dirty surfaces with Uula Washing Agent following the instructions. Allow to dry thoroughly before treating.

#### **Colourless treatment**

Treat the surface with colourless Ilona Sauna Stain 1–3 times. Sand the surface in between treatments and remove dust.

## **Coloured treatment**

Treat the surface with Ilona Sauna Stain 1–2 times to the desired opacity. To enhance endurance treat the surface 1–2 times with colourless Ilona Sauna Stain.

## Further treatment of the surface

Be really careful with all painted surfaces during the first month. Clean the surface only with soft rags and sponges that do not scratch the surface. Use only neutral washing agents. Rinse the surfaces carefully.

## Points to note

- \*Stir Ilona Sauna Stain thoroughly before and during use
- \*Reserve enough paint for a large surface in order to avoid potential colour variations in different batches.
- \*The colour of the surface to be treated must be taken into consideration when choosing translucent treatment agent. A small colour sample before the actual treatment is recommended.
- \*In all cases of uncertainty, please contact the manufacturer or a competent distributor before use.

Information in the technical specification is based on tests and practical experience. All instructions are only indicative and depend, for example, on the texture of the surface, quality, colour and previous treatments. Because we cannot control the use and working conditions of our products we take responsibility only for the quality of the product and guarantee that it is in accordance with the high standards of Uulatuote Oy. We do not take responsibility for damage caused by using the product against our instructions or intended use.

